

















OKITE®

www.okite.com

A large, light grey spiral graphic that starts from the center and expands outwards, filling the lower half of the page. It is composed of several concentric, slightly offset spiral lines.

OKITE®
Technical Data

OKITE® Technical Data

	Characteristics	Unit of Measurement	Average Value (Fine Structure)	Average Value (Large Structure)	Sample	Standards Employed
	Density	Kg/mc	2110,0	2110,0	5 x 5 x 2 cm	EN 14617-1
	Water Absorbion	C media %	0.07	0.07	5 x 5 x 2 cm	EN 14617-1
	Bending Strength	Mpa	65,7	51,7	5 x 20 x 2 cm	EN 14617-2
	Compression Strength	N/mm ²	159		7 x 7 cm ³	EN 14617-15
	Deep Abrasive Strength	mm	Max 27.5 - Min 25.5	Max 29.5 - Min 28.5	15 x 15 x 2 cm	EN 14617-4
	Thermal conductivity	W/(m*K)	2,0 ^{±0.3}	3,1 ^{±0.6}	50 x 50 x 3 cm	EN 12664
	Dimensional Stability	Δ	0,05 (Class A)	0,08 (Class A)	30 x 30 x 2 cm	EN 14617-12
	Impact Strength	Joule	11,4	4,9	20 x 20 x 2 cm	EN 14617-9
	Fire Resistance	Class	B	B		
	Frost Resistance	KMf25	107,2	102,7	20 x 5 x 2 cm	EN 14617-5
	Chemical Resistance	Classe	C4	C4	20 x 20 x 2 cm	UNI EN 14617-10
	Thermal Shock Resistance	ARf 20%	-4,1	-0,58	20x 5 x 1 cm	UNI EN 14617-6
	Colour Resistance to Light	Variation of Colour	Slight			
	Lead and Cadmium releas	mg/dm ²	0		30 x 30 x 1 cm	UNI EN ISO 10545-15

*Values stated



OKITE®

www.okite.com

EUROPE

SIC s.r.l.

Corso Vittorio Emanuele II,30
20122 MILANO (MI)
Italia

Tel.: +39 02 870 72 836

Fax: +39 02 870 72 837

USA

Seieffe Corporation

Importer & Master Distributor
12227 K FM 529
Northwoods Industrial Park
Houston - Tx 77041
United States

Tel.: +1 713 849 3800

Fax: +1 713 849 3835

Toll Free:+1 866 654 8397

UNITED KINGDOM

Seieffe UK Ltd

104 High Street London
Colney AL2 1QL
Tel. 01992 470 801
Fax. 01992 470 799